

VITEX



STANDARD TRADE NAME	Vitex
BOTANICAL NAME	Vitex Cofassus
COLOUR	Creamy yellow to dark grey
TEXTURE	Fine and even
DENSITY/STRENGTH	700-800 kg/m ³ @ 12% moisture content Class 2 Strength
DURABILITY	Class 2
SEASONING	Seasoning slow, but well with little degrade. Preferable to preliminary air dry prior to kiln drying.
WORKING QUALITIES	Vitex has good working and finishing properties
DISTRIBUTION	Vitex is a major commercial species of the Solomon Islands. A medium sized to large tree found throughout the South Western Pacific region but more a common occurrence in the North Solomons and the Solomon Islands.
USES	Building Construction F27, Furniture, Exterior posts, joinery, decking, pergolas and boatbuilding.

Auckland: 102 Main Road, Kumeu, ph: 09 412 7722, fax: 09 412 7723
Christchurch: 72 Hammersmith Drive, Sockburn, ph: 03 348 9726, fax: 03 341 0257

www.jsctimber.co.nz