



WEST AUSTRALIAN JARRAH

STANDARD TRADE NAME	Jarrah
OTHER NAMES	Western Jarrah; West Australian Jarrah
SPECIES	Eucalyptus Marginata
COLOUR	Light to dark red timber, darkening to a uniform red-brown mahogany. Juvenile wood tends towards lighter hues.
GRAIN	Includes straight and interlocked grain with even medium to coarse texture and occasional fiddleback. The grades do allow some natural defects such as gum vein and minor knots as clear wood becomes more difficult to produce.
DENSITY/STRENGTH	820 kg/m ³ @ 12% moisture content Strength group 4
DURABILITY	Heartwood – durable. Resistant to fire termite and marine borers. Class 1-2 Durability.
SEASONING	Seasons readily by air or kiln drying, although there can be some warping due to sloping grain. Pre-air drying to recommended.
WORKING QUALITIES	The timber machines and finishes well and is considered to be a superior flooring timber. Takes on excellent polish.
USES	High quality furniture, joinery, flooring and other heavy construction.

Auckland
102 Main Road, Kumeu
Ph: 09 412 7722
Fax: 09 412 7723

Christchurch
72 Hammersmith Drive, Sockburn
Ph: 03 348 9726
Fax: 03 341 0257

www.jsctimber.co.nz