

WESTERN HEMLOCK

Version 2A

STANDARD TRADE NAME	Western Hemlock
BOTANICAL NAMES	Tsuga Heterophylla
DISTRIBUTION	Canada + USA
COLOUR	Heartwood is a uniform straw colour to occasional pale brown
GRAIN	Straight grain, non-resinous with a lustrous surface and a fine, even texture
DENSITY/STRENGTH	*(500 kg/m ³)
DURABILITY	Non-Durable, Interior use only
SEASONING	Good results when dried with care. Stable in service especially when Vertical Grain
WORKING QUALITIES	Works well with hand and machine tools. Able to take on intumescent coating. Good for gluing and staining. Sharp knives essential for clean smooth finish
USES	Very useful where high grade softwood is needed indoors. Interior Joinery, Paneling, Display Screens/ Feature Battens, Boatbuilding Framing & Cleating, Ladder Rails, Mouldings, Blinds and Louvers.

Disclaimer:

JSC has endeavoured to ensure this information is accurate but recommends that for critical applications independent advice is obtained. These properties are only a guide, as timber is a natural product there will be variations within any species.

* Air dry density (kg/m³) is average indication only and actual value may vary

This information may be updated at any time.

Profiles, fixing details and documentation available by request at

specification@jsttimber.co.nz

ph: 0800 572 688