

ALASKAN YELLOW CEDAR

Version 2

STANDARD TRADE NAME	Alaskan Yellow Cedar
BOTANICAL NAMES	Chamaecyparis Nootkatensis
DISTRIBUTION	Canada
COLOUR	Heartwood – Consistent pale yellow with a fine even texture
GRAIN	Straight Grain
DENSITY/STRENGTH	*(500kg/m ³) Hard and strong
DURABILITY	Durable in service and resistant to decay, insect attack and some marine borer.
SEASONING	Shrinks little in drying, and stable in service
WORKING QUALITIES	Works well with hand and machine tools. Slightly greasy to the touch. It glues, nails, screws, stains and takes paint and varnish well. Can be brought to an excellent finish.
USES	Interior joinery, Exterior Joinery, Windows and doors, Boatbuilding, Shingles and Shakes, Cladding and Decking.

Disclaimer:

JSC has endeavoured to ensure this information is accurate but recommends that for critical applications independent advice is obtained. These properties are only a guide, as timber is a natural product there will be variations within any species.

* Air dry density (kg/m³) is average indication only and actual value may vary

This information may be updated at any time.

Profiles, fixing details and documentation available by request at

specification@jsctimber.co.nz

ph: 0800 572 688