

BLACKBUTT

Version 2

STANDARD TRADE NAME	Blackbutt
BOTANICAL NAME	Eucalyptus Pilularis
DISTRIBUTION	Good availability throughout Australian East Coastal Regions
COLOUR	Attractive colouring from cream to pale brown, sometimes with a slight tinge of pink.
GRAIN	Blackbutt is a commonly grown hardwood. Its grain is usually straight and texture is medium and even.
DENSITY/STRENGTH	*900kgs/m ³ **Janka Dry Hardness: 9.1 kN Medium shrinkage rates apply
DURABILITY	Class 1 for above ground use Class 2 for in ground use
SEASONING	Relatively easy to dry but can be prone to surface and end check if the process is hurried
WORKING QUALITIES	Blackbutt is relatively easy to work, cuts easily and is also a good to fair bending timber.
USES	Applied and structural Flooring, Decking, Paneling, Poles Sleepers, Pergolas, stairs and framework.

Disclaimer:

JSC has endeavoured to ensure this information is accurate but recommends that for critical applications independent advice is obtained. These properties are only a guide, as timber is a natural product there will be variations within any species.

* Air dry density (kg/m³) is average indication only and actual value may vary

** The Janka Dry Hardness rating measures the hardness of the wood. The higher the rating the harder the wood.

This information may be updated at any time.

Profiles, fixing details and documentation available by request at

specification@jsctimber.co.nz

ph: 0800 572 688