

IROKO

Version 2

STANDARD TRADE NAME	Iroko
BOTANICAL NAMES	Milicia Excelsa, Milicia Regia
DISTRIBUTION	Widely spread across tropical Africa.
COLOUR	Varies from pale, yellowish brown to dark, chocolate brown.
GRAIN	Medium to coarse texture, typically interlocked.
DENSITY/STRENGTH	Rated medium in all categories. *640kg/m ³ at 12%MC.
DURABILITY	Class 1-2 Durable. Will provide many years of service life.
SEASONING	Little or no risk of checking and case hardening or distortion makes this one of the easiest species to dry.
WORKING QUALITIES	Fairly high blunting affect means sharp tools are a must. Planes smoothly and glues well.
USES	One of the most versatile timbers, suitable for most interior and exterior uses i.e. Joinery, doors, handrails, flooring, decking & beams.

Disclaimer:

JSC has endeavoured to ensure this information is accurate but recommends that for critical applications independent advice is obtained. These properties are only a guide, as timber is a natural product there will be variations within any species.

* Air dry density (kg/m³) is average indication only and actual value may vary

This information may be updated at any time.

Profiles, fixing details and documentation available by request at

specification@jsctimber.co.nz

ph: 0800 572 688