

RADIATA PINE

Version 2

STANDARD TRADE NAME	Radiata Pine
BOTANICAL NAMES	Pinus Radiata, Monterey Pine
DISTRIBUTION	New Zealand
COLOUR	Heartwood is an even light brown to chestnut brown Sapwood is creamy white
GRAIN	Straight grain and a medium, even texture
DENSITY	*(460-560kg/m ³) Versatile and suitable for a wide variety of end use applications. A medium density softwood.
NATURAL DURABILITY	Non-Durable to perishable with regards to decay resistance. Treatment with preservatives is required for external application.
SEASONING	Easily processed, dried and treated.
WORKING QUALITIES	Works well with hand and machine tools. Will take staining and coating well. Used in conjunction with a range of structural adhesives.
USES	Exterior Cladding, Decking, Fencing, Window Sashes, Pergolas and Framing.

Disclaimer:

JSC has endeavoured to ensure this information is accurate but recommends that for critical applications independent advice is obtained. These properties are only a guide, as timber is a natural product there will be variations within any species.

*Air dry density (kg/m³) is average indication only and actual value may vary
This information may be updated at any time.

Profiles, fixing details and documentation available by request at

specification@jsctimber.co.nz

ph: 0800 572 688